

TEST REPORT IZVEŠTAJ O ISPITIVANJIMA

LOW DENSITY POLYETHYLENE POLIETILEN NISKE GUSTINE

HIPTEN 22003

Lot N° 22/23

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m ³	922	920 - 923
2.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO1133-1 SRPS EN ISO1133-1	g/10 min	0,28	0,27-0,35
3.	*Colour, average BOJA GRANULA	Internal method MA0724-UP010	/	STW	STW
4.	*Colored granules OBOJENE GRANULE	Internal method MA0724-UP010	No gr/250g	⁽¹⁾ 34gr -1G 33gr 1G	max 10% 1G/1Y

*Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja

Note:

STW – Standard white / Standardna bela boja

⁽¹⁾gr – Granules / Granule


G – Gray colored (-1G – light gray, 1G – gray / Sivo obojenje (-1G – svetlo siva, 1G - siva):

34 granule -1G (light gray colored) in 250 g of sample / 34 granula -1G (svetlo sivo obojeno) u 250 g uzorka

33 granule 1G (gray colored) in 250 g of sample / 33 granula 1G (sivo obojeno) u 250 g uzorka

Pancevo, 24.01.2023.

Department Director / Direktor RJL


Branka Mijusković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj Izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259
Business bank: Banca Intesa, Beograd, M. Popovica 7B, Account No. 160-9629-95
ID Number: 08064300
VAT No: 101052694

