

## TEST REPORT IZVEŠTAJ O ISPITIVANJIMA

### LOW DENSITY POLYETHYLENE POLIETILEN NISKE GUSTINE

**HIPTEN 22003**

**Lot N° 34123**

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m <sup>3</sup>	921	920 - 923
2.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO 1133-1 SRPS EN ISO 1133-1	g/10 min	0,28	0,27 - 0,35
3.	*Film structure irregularities IZGLED FILMA	Internal method MA0724-UP011	/	(1) 9C	max 6A/6B/8C/5D

*\*Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja*

Notes:

(1) Film structure irregularities on the scale 4 – 10 / nepravilnosti filma na skali 4 – 10

A – arrowheads / nepravilnosti u obliku strelice


B – pinpoint gels / tačkasti gelovi

C – gels / gelovi

D – oxidized gels / oksidovani gelovi

Pancevo, 09.05.2023

Department Director / Direktor RJL

  
Branka Mijušković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj Izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259  
Business bank: Banca Intesa, Beograd, M. Popovica 7B, Account No. 160-9629-95  
ID Number: 08064300  
VAT No: 101052694

