

## TEST REPORT IZVEŠTAJ O ISPITIVANJIMA

### LOW DENSITY POLYETHYLENE POLIETILEN NISKE GUSTINE

**HIPTEN 22003**

**Lot N° 74522**

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m <sup>3</sup>	922	920 - 923
2.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO1133-1 SRPS EN ISO1133-1	g/10 min	0,28	0,27 – 0,35
3.	Colour, average BOJA GRANULA	Internal method MA0724-UP010	/	STW	STW
4.	Colored granules OBOJENE GRANULE	Internal method MA0724-UP010	No gr/250g	*20 gr +1G	max 10% 1G

Note:

STW – Standard white / Standardna bela boja


\*gr – Granules / Granule

G – Gray colored (1G – gray, / Sivo obojenje (1G – siva):

20 granule +1G (gray colored) in 250 g of sample / 20 granula +1G (sivo obojena) u 250 g uzorka

Pančevo, 24.10.2022.

Department Director / Direktor RJL

  
Branka Mijusković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259  
Business bank: Banca Intesa, Beograd, M. Popovica 7B, Account No. 160-9629-95  
ID Number: 08064300  
VAT No: 101052694

