

## TEST REPORT IZVEŠTAJ O ISPITIVANJIMA

### HIGH DENSITY POLYETHYLENE POLIETILEN VISOKE GUSTINE

**HIPLEX HXM 50100**

**Lot N° 150421**

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Melt flow rate 190°C/21,6 kg MASENI PROTOK RASTOPA	EN ISO 1133-1, SRPS EN ISO 1133-1	g/10 min	9,7	8,0 – 12,0
2.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m <sup>3</sup>	951	948 - 951
3.	Resin Appearance-specks in/on the granules MRLJE U/NA GRANULAMA	Internal method MA0724-UP010	No gr/250g	*1z/3c2z	max 4

Note:

\*Number of yellow (z) and black (c) specks in/on the granules in 250g of the sample / Broj žutih (z) i crnih (c) mrlja u/na granulama u 250g uzorka


gr - granules/granule

z - yellow speck / žuta mrlja

c - black speck / crne mrlje

Pančevo, 26.10.2021.

Department Director / Direktor RJL

  
Branka Mijušković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259  
Business bank: Banca Intesa, Beograd, M. Popovica 7B, Account No. 160-9629-95  
ID Number: 08064300  
VAT No: 101052694

