

**TEST REPORT**  
**IZVEŠTAJ O ISPITIVANJIMA****LOW DENSITY POLYETHYLENE**  
**POLIETILEN NISKE GUSTINE****HIPTEN 21018A6****Lot N° 15024**

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	<b>Melt flow rate 190°C/2,16 kg</b> MASENI PROTOK RASTOPA	<b>EN ISO1133-1</b> SRPS EN ISO1133-1	g/10 min	2.0	1.8 - 2.2
2.	<b>Density</b> GUSTINA	<b>EN ISO 1183-2</b> SRPS EN ISO 1183-2	kg/m <sup>3</sup>	922	920 - 923
3.	<b>*Film structure irregularities</b> IZGLED FILMA	<b>Internal method</b> MA0724-UP011	/	<sup>(1)</sup> 4A/5B/7C	max 4A/5B/6C/4D

**\*Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja**  
Notes:

<sup>(1)</sup>Film structure irregularities on the scale 4 – 10 / nepravilnosti filma na skali 4 – 10


A – arrowheads / nepravilnosti u obliku strelice

B – pinpoint gels / tačkasti gelovi

**C – gels / gelovi**

D – oxidized gels / oksidovani gelovi

Pancevo, 28.02.2024

 Director of Laboratory Petrohemija /  
Direktor Laboratorija Petrohemija  
Branka Mijušković

This report is issued only for the purpose of the tender / Ovaj Izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259

Business bank: Banca Intesa, Beograd, M. Popovica 7B,

Account No. 160-9629-95

CRN: 08064300; TIN: 101052694

