

TEST REPORT
IZVEŠTAJ O ISPITIVANJIMA**LOW DENSITY POLYETHYLENE**
POLIETILEN NISKE GUSTINE**HIPTEN 21018A6****Lot N° 16225**

| N° R. br. | Analyzed parameters ISPITIVANJE | Method METODA | Unit JEDINICA | Value VREDNOST | Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU |
|--------------|---|-------------------------------------|-------------------|-------------------|--|
| 1. | Density GUSTINA | EN ISO 1183-2 SRPS EN ISO 1183-2 | kg/m ³ | 922 | 920 - 923 |
| 2. | Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA | EN ISO1133-1 SRPS EN ISO1133-1 | g/10 min | 2.0 | 1.8 – 2.2 |
| 3. | *Haze MUTNOĆA FILMA | ASTM D1003 | % | *10.8 | max 10 |

**Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja*
Notes:

Pancevo, 17.04.2025

Department Manager /
Rukovodilac Laboratorije Petrohemija
Branka Mijušković

This report is issued only for the purpose of the tender / Ovaj Izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259
Business bank: Banca Intesa, Beograd, M. Popovica 7B,
Account No. 160-9629-95
CRN: 08064300; TIN: 101052694

