

TEST REPORT IZVEŠTAJ O ISPITIVANJIMA

LOW DENSITY POLYETHYLENE POLIETILEN NISKE GUSTINE

HIPTEN 22003

Lot N° 8823

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m ³	922	920 - 923
2.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO1133-1 SRPS EN ISO1133-1	g/10 min	0,30	0,27-0,35
3.	*Colour, average BOJA GRANULA	Internal method MA0724-UP010	/	STW	STW
4.	*Colored granules OBOJENE GRANULE	Internal method MA0724-UP010	No gr/250g	⁽¹⁾ 15 gr 1G	max 10% 1G/1Y

*Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja

Note:

STW – Standard white / Standardna bela boja


⁽¹⁾gr – Granules / Granule

G – Gray colored (1G – gray) / Sivo obojenje (1G – siva)

15 granule 1G (gray colored) in 250 g of sample / 15 granula 1G (sivo obojeno) u 250 g uzorka

Pančevo, 03.02.2023.

Department Director / Direktor RJL


Branka Mijušković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj izveštaj se izdaje samo za potrebe tendera