

TEST REPORT
IZVEŠTAJ O ISPITIVANJIMA**LOW DENSITY POLYETHYLENE**
POLIETILEN NISKE GUSTINE**HIPTEN 21018A6****Lot N° 6124**

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO1133-1 SRPS EN ISO1133-1	g/10 min	2.0	1.8 - 2.2
2.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m ³	921	920 - 923
3.	*Antiblock additive content SADRŽAJ ANTIBLOK ADITIVA	Internal method MA0745-UP004	µg/g	410	500-700

**Tests that are not within the scope of accreditation / Ispitivanja koja nisu iz obima akreditovanja*

Pancevo, 31.01.2024

Director of Laboratory Petrohemija /
Direktor Laboratorija Petrohemija

Branka Mijušković

This report is issued only for the purpose of the tender / Ovaj Izveštaj se izdaje samo za potrebe tendera

Register of Business Entities in Serbian Business Register Agency - No. 259
Business bank: Banca Intesa, Beograd, M. Popovica 7B,
Account No. 160-9629-95
CRN: 08064300; TIN: 101052694