

TEST REPORT

IZVEŠTAJ O ISPITIVANJIMA

LOW DENSITY POLYETHYLENE

POLIETILEN NISKE GUSTINE

HIPTEN 22003

Lot N° 94422

N° R. br.	Analyzed parameters ISPITIVANJE	Method METODA	Unit JEDINICA	Value VREDNOST	Specification for prime grade SPECIFICIRANA VREDNOST ZA PRVU KLASU
1.	Density GUSTINA	EN ISO 1183-2 SRPS EN ISO 1183-2	kg/m ³	921	920 - 923
2.	Melt flow rate 190°C/2,16 kg MASENI PROTOK RASTOPA	EN ISO1133-1 SRPS EN ISO1133-1	g/10 min	0,32	0,27-0,35
3.	Colour, average BOJA GRANULA	Internal method MA0724-UP010	/	STW	STW
4.	Colored granules OBOJENE GRANULE	Internal method MA0724-UP010	No gr/250g	⁽¹⁾ 20gr 1G 5gr 2G	max 10%1G/1Y
5.	Resin Appearance-specks in/on the granules MRLJE U/NA GRANULAMA	Internal method MA0724-UP010	No gr/250g	⁽²⁾ 2c/5c	max 6

Note:

STW – Standard white / Standardna bela boja

⁽¹⁾gr – Granules / Granule

G – Gray colored (1G – gray, 2G – dark gray) / Sivo obojenje (1G-siva, 2G – tamno siva):


20 granule 1G (gray colored), 5 granule 2G (dark gray colored) in 250 g of sample / 20 granula 1G (sivo obojeno), 5 granula 2G (tamno sivo obojeno) u 250 g uzorka

⁽²⁾Number of black (c) specks in/on the granules in 250g of the sample / Broj crnih (c) mrlja u/na granulama u 250g uzorka

c – black speck / crne mrlje

Pancevo, 12.12.2022.

Department Director / Direktor RJL


Branka Mijušković, MSc.Chem.Eng

This report is issued only for the purpose of the tender / Ovaj izveštaj se izdaje samo za potrebe tendera